

# CoCrMo

Cobalt, chromium, and molybdenum alloy designated for medical, denture and high-temperature applications

## Key Features:

- > Excellent biocompatibility
- > Good heat resistance, thermal fatigue resistance and mechanical properties at elevated temperature
- > Excellent oxidation resistance
- > Great as-finished surface

## [ Technical Data ]

### General Properties

<b>Density</b> <small>ISO3369</small>	≥ 8.35 g/cm <sup>3</sup>
---------------------------------------	--------------------------

### Mechanical Properties

(As built)

<b>Tensile Strength</b> <small>ISO6892-1</small>	≥ 1060 MPa
--	------------

<b>Yield Strength</b> <small>ISO6892-1</small>	≥ 800 MPa
--	-----------

<b>Elongation after Fracture</b> <small>ISO6892-1</small>	≥ 8 %
---	-------

<b>Vickers hardness</b> <small>ISO6507-1</small>	n/a
--	-----

### Mechanical Properties <sup>1</sup>

(Heat treated)

<b>Tensile Strength</b> <small>ISO6892-1</small>	≥ 970 MPa
--	-----------

<b>Yield Strength</b> <small>ISO6892-1</small>	≥ 620 MPa
--	-----------

<b>Elongation after Fracture</b> <small>ISO6892-1</small>	≥ 12 %
---	--------

<b>Vickers hardness</b> <small>ISO6507-1</small>	≥ 310 HV5/15
--	--------------


<sup>1</sup> For more information on heat treatment process, please contact us directly.

Farsoon systems are open material platform. For special materials such as tungsten, tantalum and pure copper, please contact us with your inquiries or requirements.

Disclaimer: Many factors may affect the performance characteristics of products. We recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. Farsoon makes no warranties of any type, express or implied, including but not limited to, the warranties of merchantability or fitness for a particular use. This also applies regarding the consideration of possible intellectual property rights as well as laws and regulations. Farsoon reserves the right to change the technical data without notice. Farsoon®, Buildstar®, Makestar® are registered trademarks of Farsoon Technologies. Last Change: 2022-01-29

## Example Applications:

- > Ideal for production of removable partial denture (PRD) parts.
- > Most important materials used in orthopedic applications, i.e., total hip replacements
- > High-temperature applications



RPD( Removable Partial Denture)  
System: FS121M

[www.farsoon.com](http://www.farsoon.com)